



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Memory M-Acres

Date: 25-Sep-20  
Shear ID: 204375  
Test No: 500646


### Animal and Sample Description

Animal Name: RDE'S MASERATI LIMITED EDITION  
Registry #: 35300366  
Breed: Suri  
Sex: Male  
Colour: 100 - White

Date of Birth (Age): 21-Jun-17  
Sample Location: GRID  
Sample Date: 27-Apr-20  
Previous Shear Date: 29-Apr-19  
Total Fleece Wt (lbs): 5.88

### Laboratory Data

Mean Fiber Diameter:	22.6 microns	Mean Staple Length:	139 mm
Standard Deviation:	5.1 microns	Length Standard Deviation:	11.6 mm
Coefficient of Variation:	22.7 %	Length Coefficient of Variation:	8.3 %
Spin Fineness:	22.3 microns	Mean Curvature:	8.9 deg/mm
Fibers Greater Than 30 microns:	6.9 %	SD Curvature:	13.7 deg/mm
Comfort Factor:	93.1 %	Medullated Fibers:	15.5 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)