



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sopris Alpaca Farm
35795 Highway 6, Silt
CO 81652, US

Date: 5-Sep-22
Shear ID:
Test No: 610057


Animal and Sample Description

Animal Name: Grace
Registry #:
Breed:
Sex:
Colour:

Date of Birth (Age):
Sample Location:
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	19.4 microns	Comfort Factor:	98.5 %
Standard Deviation:	3.9 microns	Mean Curvature:	44.8 deg/mm
Coefficient of Variation:	20.0 %	SD Curvature:	34.4 deg/mm
Spin Fineness:	18.7 microns		
Fibers Greater Than 30 microns:	1.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com