

## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Odin Falls Alpacas 9101 NW 31st ST Terrebonne, OR 97760-9443 US			Date: Shear ID: Test No:	4-Nov-20 206976 501167	
		Animal and Sa	mple Description		
Animal Name: Registry #: Breed: Sex: Colour:	ODINS Steppin up Dude 35511816 Hauacaya Male 205 - Dark Fawn		Date of Birth (Age): Sample Location: Sample Date: Previous Shear Date: Total Fleece Wt (Ibs):	30-Aug-18 GRID 1-May-20 11-May-19 8.00	
		Labora	itory Data		
Mean Fiber Diameter: Standard Deviation: Coefficient of Variation: Spin Fineness: Fibers Greater Than 30 microns: Comfort Factor:		20.5 microns 3.8 microns 18.4 % 19.5 microns 1.1 % 98.9 %	Mean Staple Length: Length Standard Deviation: Length Coefficient of Variation: Mean Curvature: SD Curvature: Medullated Fibers:		102 mm 2.8 mm 2.7 % 41.1 deg/mm 22.0 deg/mm %
12%					
10% 8% 5					
ati					
Percent of Observations %9 %9 %9 %9 %9 %9 %9 %9 %9 %9 %9 %9 %9					
Bercent of Observatit 4%					

## Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear **Business Manager** 

Hund

Jude Davidson Authorised Signatory

SGS General Terms and Conditions

The validity of this document may be confirmed by contacting the address shown below SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com