


# LAMBORGHINI ENGINE

**AFD:** 20.6  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 22.7 %  
**CF:** 96.9 %  
**Curve:** 31.5 Dg/mm  
**Min:** 19.4  $\mu$   
**Max:** 22.4  $\mu$   
**Staple:** 100.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# LAMBORGHINI ENGINE

**AFD:** 20.6  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 22.7 %  
**CF:** 96.9 %  
**Curve:** 31.5 Dg/mm  
**Min:** 19.4  $\mu$   
**Max:** 22.4  $\mu$   
**Staple:** 100.0 mm

