



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Grazing Hills Ranch
1042 Four Mile Rd, Viola
ID 83872, US

Date: 3-Sep-21
Shear ID:
Test No: 604365


Animal and Sample Description

Animal Name: Ephraim
Registry #: 32648096
Breed:
Sex: Male
Colour: 500 - True Black

Date of Birth (Age): 24-Jul-12
Sample Location:
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	18.0 microns	Comfort Factor:	96.8 %
Standard Deviation:	4.6 microns	Mean Curvature:	49.6 deg/mm
Coefficient of Variation:	25.5 %	SD Curvature:	37.8 deg/mm
Spin Fineness:	18.3 microns		
Fibers Greater Than 30 microns:	3.2 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com