



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Grazing Hill Alpacas
1042 Four Mile Rd, Viola
ID 83872, US

Date: 22-Jul-22
Shear ID:
Test No: 608608


Animal and Sample Description

Animal Name: Treasure's Tempest
Registry #:
Breed:
Sex: Male
Colour: 202 - Light Fawn

Date of Birth (Age): 14-Sep-18
Sample Location:
Sample Date: 25-May-22
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	23.8 microns	Comfort Factor:	89.8 %
Standard Deviation:	5.1 microns	Mean Curvature:	44.7 deg/mm
Coefficient of Variation:	21.4 %	SD Curvature:	35.6 deg/mm
Spin Fineness:	23.3 microns	Medullated Fibers:	24.4 %
Fibers Greater Than 30 microns:	10.2 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com