



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Lesley Anne Ezelle
28228 NE Reilly Road
Camas, WA 98607 US

Date: 7-Oct-20
Shear ID:
Test No: 500938


Animal and Sample Description

Animal Name: chaja 2020
Registry #:
Breed:
Sex:
Colour:

Date of Birth (Age):
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	22.9 microns	Mean Staple Length:	111 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	5.7 mm
Coefficient of Variation:	17.7 %	Length Coefficient of Variation:	5.1 %
Spin Fineness:	21.7 microns	Mean Curvature:	27.0 deg/mm
Fibers Greater Than 30 microns:	4.1 %	SD Curvature:	15.6 deg/mm
Comfort Factor:	95.9 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool@sgs.com Web: www.wooltesting.sgs.com