



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Northern Blessings Alpacas
12942 Ringer Rd, Rapid City
MI 49676, US

Date: 17-Mar-23
Shear ID: 245514
Test No: 611193


Animal and Sample Description

Animal Name: Michelangelo's IL Divino
Registry #: 36095131
Breed: Huacaya
Sex: Male
Colour: 201 - Beige

Date of Birth (Age): 30-Jul-21
Sample Location: GRID
Sample Date: 20-May-22
Previous Shear Date: 21-May-21
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	17.3 microns	Mean Staple Length:	116 mm
Standard Deviation:	5.1 microns	Length Standard Deviation:	2.1 mm
Coefficient of Variation:	29.6 %	Length Coefficient of Variation:	1.8 %
Spin Fineness:	18.2 microns	Mean Curvature:	53.7 deg/mm
Fibers Greater Than 30 microns:	2.4 %	SD Curvature:	23.7 deg/mm
Comfort Factor:	97.6 %	Medullated Fibers:	5.0 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com