


AFD: 26.6 μ
SD: 5.3 μ
CV: 20.0 %
CF: 82.0 %
Curve: 32.1 Dg/mm
Min: 25.0 μ
Max: 28.6 μ
Staple: 100.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

LBCA'S FLINT

AFD: 26.6 μ
SD: 5.3 μ
CV: 20.0 %
CF: 82.0 %
Curve: 32.1 Dg/mm
Min: 25.0 μ
Max: 28.6 μ
Staple: 100.0 mm

