


AFD: 22.0 μ
SD: 5.6 μ
CV: 25.4 %
CF: 92.1 %
Curve: 35.5 Dg/mm
Min: 18.3 μ
Max: 24.8 μ
Staple: 115.0 mm

% of Fibers




Alpaca Fiber Testing USA

Fiber Diameter (microns)

HMTA ROYAL AKU

AFD: 22.0 μ
SD: 5.6 μ
CV: 25.4 %
CF: 92.1 %
Curve: 35.5 Dg/mm
Min: 18.3 μ
Max: 24.8 μ
Staple: 115.0 mm



Alpaca Fiber Testing USA