



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Triple Diamonds Alpaca Ranch
3275 E Schafer Rd. Howell
MI 48843-9422, US

Date: 28-Oct-22
Shear ID: 242473
Test No: 610661


Animal and Sample Description

Animal Name: Alpaca Palace's Zinging Bells
Registry #: 35460473
Breed: Huacaya
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 2-Mar-20
Sample Location: GRID
Sample Date: 7-May-22
Previous Shear Date: 27-Apr-21
Total Fleece Wt (lbs): 5.50

Laboratory Data

Mean Fiber Diameter:	20.6 microns	Mean Staple Length:	121 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	8.3 mm
Coefficient of Variation:	16.7 %	Length Coefficient of Variation:	6.8 %
Spin Fineness:	19.4 microns	Mean Curvature:	50.8 deg/mm
Fibers Greater Than 30 microns:	1.0 %	SD Curvature:	20.4 deg/mm
Comfort Factor:	99.0 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com