



**Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report**

Briarwood Acres
4150 Briarwood NW St
OR 97304-9541, US

Date: 20-Oct-22
Shear ID: 243631
Test No: 610441


Animal and Sample Description

Animal Name: Ssky Accoyo Chasidy
Registry #: 30831155
Breed: Suri
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 3-Jun-11
Sample Location: GRID
Sample Date: 24-Jun-22
Previous Shear Date: 23-May-21
Total Fleece Wt (lbs): 6.0625

Laboratory Data

Mean Fiber Diameter:	27.5 microns	Mean Staple Length:	114 mm
Standard Deviation:	6.6 microns	Length Standard Deviation:	10.7 mm
Coefficient of Variation:	24.1 %	Length Coefficient of Variation:	9.4 %
Spin Fineness:	27.5 microns	Mean Curvature:	27.8 deg/mm
Fibers Greater Than 30 microns:	22.0 %	SD Curvature:	12.1 deg/mm
Comfort Factor:	78.0 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kibbirie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com