



**Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report**

Briarwood Acres
4150 Briarwood NW St
OR 97304-9541, US

Date: 20-Oct-22
Shear ID: 243627
Test No: 610437


Animal and Sample Description

Animal Name: Briarwood's Copper By Bravo
Registry #: 35523574
Breed: Suri
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 2-Jun-19
Sample Location: GRID
Sample Date: 24-Jun-22
Previous Shear Date: 23-May-21
Total Fleece Wt (lbs): 10.0625

Laboratory Data

Mean Fiber Diameter:	31.6 microns	Mean Staple Length:	213 mm
Standard Deviation:	6.9 microns	Length Standard Deviation:	15.0 mm
Coefficient of Variation:	21.9 %	Length Coefficient of Variation:	7.1 %
Spin Fineness:	31.0 microns	Mean Curvature:	27.6 deg/mm
Fibers Greater Than 30 microns:	51.5 %	SD Curvature:	13.1 deg/mm
Comfort Factor:	48.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com