



**Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report**

Briarwood Acres
4150 Briarwood Street, Salem
NH, 97304 US

Date: 30-Jul-21
Shear ID: 222571
Test No: 603394


Animal and Sample Description

Animal Name: Briarwood's Kokoleka by Bravo
Registry #: 35309628
Breed: Suri
Sex: Female
Colour: 209 - Light Brown

Date of Birth (Age): 18-Jul-19
Sample Location: GRID
Sample Date: 23-May-21
Previous Shear Date: 30-May-20
Total Fleece Wt (lbs): 6.10

Laboratory Data

Mean Fiber Diameter:	25.8 microns	Mean Staple Length:	189 mm
Standard Deviation:	6.6 microns	Length Standard Deviation:	7.6 mm
Coefficient of Variation:	25.4 %	Length Coefficient of Variation:	4.0 %
Spin Fineness:	26.2 microns	Mean Curvature:	29.0 deg/mm
Fibers Greater Than 30 microns:	14.2 %	SD Curvature:	15.8 deg/mm
Comfort Factor:	85.8 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com