



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Elizabeth Turner
15414 140th St, Foreston
MN 56330-9541, US

Date: 11-Aug-23
Shear ID: 253005
Test No: 614093

Animal and Sample Description


Animal Name: Baldassare's Private Reserve of TTA
Registry #: 35524502
Breed: Huacaya
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 12-Oct-19
Sample Location: GRID
Sample Date: 3-May-23
Previous Shear Date: 19-May-22
Total Fleece Wt (lbs): 8.2

Laboratory Data

Mean Fiber Diameter: 19.7 microns
Standard Deviation: 4.2 microns
Coefficient of Variation: 21.4 %
Spin Fineness: 19.2 microns
Fibers Greater Than 30 microns: 2.2 %
Comfort Factor: 97.8 %

Mean Staple Length: 72 mm
Length Standard Deviation: 3.8 mm
Length Coefficient of Variation: 5.3 %
Mean Curvature: 49.7 deg/mm
SD Curvature: 28.9 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com