



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Spross Hollow Alpacas
7218 Exeter Ave, Spring Branch
AL, 78070, US

Date: 27-May-21
Shear ID:
Test No: 601570


Animal and Sample Description

Animal Name: Mairzy
Registry #: 36015375
Breed: Huacaya
Sex: Male
Colour: 211 - Medium Rose Grey

Date of Birth (Age): 10-Feb-20
Sample Location: GRID
Sample Date: 3-Apr-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	21.5 microns	Mean Staple Length:	77 mm
Standard Deviation:	4.2 microns	Length Standard Deviation:	6.3 mm
Coefficient of Variation:	19.4 %	Length Coefficient of Variation:	8.2 %
Spin Fineness:	20.6 microns	Mean Curvature:	46.0 deg/mm
Fibers Greater Than 30 microns:	1.6 %	SD Curvature:	18.5 deg/mm
Comfort Factor:	98.4 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com