



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Spross Hollow Alpacas
7218 Exeter Ave, Spring Branch
AL, 78070, US

Date: 27-May-21
Shear ID:
Test No: 601577


Animal and Sample Description

Animal Name: Black Tie
Registry #: 35068365
Breed: Huacaya
Sex: Male
Colour: 500 - True Black

Date of Birth (Age): 22-Dec-16
Sample Location: GRID
Sample Date: 3-Apr-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	24.0 microns	Mean Staple Length:	85 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	1.6 mm
Coefficient of Variation:	17.0 %	Length Coefficient of Variation:	1.8 %
Spin Fineness:	22.6 microns	Mean Curvature:	42.7 deg/mm
Fibers Greater Than 30 microns:	5.4 %	SD Curvature:	16.0 deg/mm
Comfort Factor:	94.6 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com