



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Suri & Company
6 Clermont Lane, Saint Louis
MO 63124, US

Date: 22-Jul-21
Shear ID: 222419
Test No: 602971


Animal and Sample Description

Animal Name: Goldyn Rae's Yara
Registry #: 35493303
Breed: Suri
Sex: Female
Colour: 100 - White

Date of Birth (Age): 4-Jun-19
Sample Location: GRID
Sample Date: 13-Apr-21
Previous Shear Date:
Total Fleece Wt (lbs): 11.80

Laboratory Data

Mean Fiber Diameter:	21.8 microns	Mean Staple Length:	226 mm
Standard Deviation:	5.4 microns	Length Standard Deviation:	3.5 mm
Coefficient of Variation:	24.8 %	Length Coefficient of Variation:	1.6 %
Spin Fineness:	21.9 microns	Mean Curvature:	30.9 deg/mm
Fibers Greater Than 30 microns:	6.4 %	SD Curvature:	13.1 deg/mm
Comfort Factor:	93.6 %	Medullated Fibers:	14.5 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com