



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Suri & Company
6 Clermont Lane, St. Louis
MO 63124. US

Date: 29-Jul-22
Shear ID: 238152
Test No: 608845

Animal and Sample Description


Animal Name: Goldyn Rae's Leda
Registry #: 35222859
Breed: Suri
Sex: Female
Colour: 100 - White

Date of Birth (Age): 16-Sep-16
Sample Location: GRID
Sample Date: 11-May-22
Previous Shear Date: 13-Apr-21
Total Fleece Wt (lbs): 8.2

Laboratory Data

Mean Fiber Diameter: 22.6 microns
Standard Deviation: 5.6 microns
Coefficient of Variation: 24.7 %
Spin Fineness: 22.7 microns
Fibers Greater Than 30 microns: 9.2 %
Comfort Factor: 90.8 %

Mean Staple Length: 185 mm
Length Standard Deviation: 4.0 mm
Length Coefficient of Variation: 2.2 %
Mean Curvature: 32.6 deg/mm
SD Curvature: 15.8 deg/mm
Medullated Fibers: 11.6 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com