



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Cotton Creek Farms
11885 Jewell Road, Thompsonville
MI 49683, US

Date: 1-Aug-22
Shear ID: 239305
Test No: 608859


Animal and Sample Description

Animal Name: Oas Xxxtreme Daredevil XXX
Registry #: 35589334
Breed: Huacaya
Sex: Male
Colour: 410 - Dark Brown

Date of Birth (Age): 15-Aug-18
Sample Location: GRID
Sample Date: 16-May-22
Previous Shear Date: 12-May-21
Total Fleece Wt (lbs): 8.6

Laboratory Data

Mean Fiber Diameter:	23.7 microns	Mean Staple Length:	101 mm
Standard Deviation:	4.8 microns	Length Standard Deviation:	2.9 mm
Coefficient of Variation:	20.4 %	Length Coefficient of Variation:	2.9 %
Spin Fineness:	22.9 microns	Mean Curvature:	53.8 deg/mm
Fibers Greater Than 30 microns:	7.3 %	SD Curvature:	21.6 deg/mm
Comfort Factor:	92.7 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com