


# MAPLE RIDGE KEYS

**AFD:** 22.9  $\mu$   
**SD:** 4.2  $\mu$   
**CV:** 18.2 %  
**CF:** 95.3 %  
**Curve:** 35.8 Dg/mm  
**Min:** 21.4  $\mu$   
**Max:** 24.0  $\mu$   
**Staple:** 130.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# MAPLE RIDGE KEYS

**AFD:** 22.9  $\mu$   
**SD:** 4.2  $\mu$   
**CV:** 18.2 %  
**CF:** 95.3 %  
**Curve:** 35.8 Dg/mm  
**Min:** 21.4  $\mu$   
**Max:** 24.0  $\mu$   
**Staple:** 130.0 mm

