



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ariya Alpacas
411 Chemin De Brill, RR22 Bolten-Quest
QC J0E 2T0, CA

Date: 12-Jun-23
Shear ID:
Test No: 612446


Animal and Sample Description

Animal Name: Ariya Belenis' Inspired Dream
Registry #: 36185054
Breed:
Sex: Female
Colour: 100 - White

Date of Birth (Age): 18-Jul-22
Sample Location: Left side
Sample Date:
Previous Shear Date: 26-Jul-22
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	13.7 microns	Comfort Factor:	99.9 %
Standard Deviation:	3.9 microns	Mean Curvature:	59.3 deg/mm
Coefficient of Variation:	28.4 %	SD Curvature:	45.3 deg/mm
Spin Fineness:	14.3 microns	Medullated Fibers:	1.4 %
Fibers Greater Than 30 microns:	0.1 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com