


# TAZA FROM MARS

**AFD:** 22.5  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 21.2 %  
**CF:** 93.4 %  
**Curve:** 24.6 Dg/mm  
**Min:** 18.8  $\mu$   
**Max:** 26.0  $\mu$   
**Staple:** 90.0 mm

% of Fibers




*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# TAZA FROM MARS

**AFD:** 22.5  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 21.2 %  
**CF:** 93.4 %  
**Curve:** 24.6 Dg/mm  
**Min:** 18.8  $\mu$   
**Max:** 26.0  $\mu$   
**Staple:** 90.0 mm



*Alpaca Fiber Testing USA*