



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Wrights Canyon River Ranch
280 Lampe Rd, Selah
WA 98942, US

Date: 6-Jul-23
Shear ID: 249409
Test No: 613117


Animal and Sample Description

Animal Name: Uber's Topper
Registry #: 35365013
Breed: Suri
Sex: Male
Colour: 100 - White

Date of Birth (Age): 23-Jun-17
Sample Location: GRID
Sample Date: 18-Apr-23
Previous Shear Date: 27-Apr-22
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	33.4 microns	Mean Staple Length:	150 mm
Standard Deviation:	8.7 microns	Length Standard Deviation:	2.2 mm
Coefficient of Variation:	26.2 %	Length Coefficient of Variation:	1.4 %
Spin Fineness:	34.1 microns	Mean Curvature:	26.6 deg/mm
Fibers Greater Than 30 microns:	58.9 %	SD Curvature:	8.0 deg/mm
Comfort Factor:	41.1 %	Medullated Fibers:	22.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com