



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Wrights Canyon River Ranch
280 Lampe Rd, Selah
WA 98942, US

Date: 6-Jul-23
Shear ID: 249399
Test No: 613107


Animal and Sample Description

Animal Name: Firestorm Veil
Registry #: 36038725
Breed: Huacaya
Sex: Female
Colour: 301 - Medium Brown

Date of Birth (Age): 17-Jul-19
Sample Location: GRID
Sample Date: 18-Apr-23
Previous Shear Date: 27-Apr-22
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	24.4 microns	Mean Staple Length:	95 mm
Standard Deviation:	5.2 microns	Length Standard Deviation:	6.5 mm
Coefficient of Variation:	21.2 %	Length Coefficient of Variation:	6.9 %
Spin Fineness:	23.7 microns	Mean Curvature:	43.5 deg/mm
Fibers Greater Than 30 microns:	10.6 %	SD Curvature:	16.8 deg/mm
Comfort Factor:	89.4 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com