



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Rhonda Deschner
PO Box 919, Wimberley
TX 78676, US

Date: 10-Jun-22
Shear ID: 234648
Test No: 607533


Animal and Sample Description

Animal Name: TP Quetzal
Registry #: 35456858
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 15-May-21
Sample Location: GRID
Sample Date: 2-May-22
Previous Shear Date: 15-Jun-21
Total Fleece Wt (lbs): 6.4

Laboratory Data

Mean Fiber Diameter:	18.2 microns	Mean Staple Length:	133 mm
Standard Deviation:	4.0 microns	Length Standard Deviation:	9.8 mm
Coefficient of Variation:	21.8 %	Length Coefficient of Variation:	7.3 %
Spin Fineness:	17.8 microns	Mean Curvature:	48.5 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	19.4 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	3.3 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com