



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Rhonda Deschner
PO Box 919, Wimberley
TX 78676, US

Date: 10-Jun-22
Shear ID: 234646
Test No: 607555


Animal and Sample Description

Animal Name: TP Allure
Registry #: 35456834
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 14-Apr-21
Sample Location: GRID
Sample Date: 2-May-22
Previous Shear Date: 15-Jun-21
Total Fleece Wt (lbs): 5.5

Laboratory Data

Mean Fiber Diameter:	18.2 microns	Mean Staple Length:	108 mm
Standard Deviation:	3.8 microns	Length Standard Deviation:	0.8 mm
Coefficient of Variation:	20.9 %	Length Coefficient of Variation:	0.7 %
Spin Fineness:	17.7 microns	Mean Curvature:	57.4 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	24.1 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	1.5 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com