


# PURPLE POST'S JERSEY DEVIL

**AFD:** 22.3  $\mu$   
**SD:** 4.4  $\mu$   
**CV:** 19.8 %  
**CF:** 94.6 %  
**Curve:** 39.0 Dg/mm  
**Min:** 21.4  $\mu$   
**Max:** 23.9  $\mu$   
**Staple:** 75.0 mm


% of Fibers



*Alpaca Fiber Testing USA*

# PURPLE POST'S JERSEY DEVIL

**AFD:** 22.3  $\mu$   
**SD:** 4.4  $\mu$   
**CV:** 19.8 %  
**CF:** 94.6 %  
**Curve:** 39.0 Dg/mm  
**Min:** 21.4  $\mu$   
**Max:** 23.9  $\mu$   
**Staple:** 75.0 mm



*Alpaca Fiber Testing USA*