


WINDY'S JOSIE

AFD: 24.7 μ
SD: 5.4 μ
CV: 21.7 %
CF: 86.4 %
Curve: 39.8 Dg/mm
Min: 24.1 μ
Max: 26.2 μ
Staple: 70.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S JOSIE

AFD: 24.7 μ
SD: 5.4 μ
CV: 21.7 %
CF: 86.4 %
Curve: 39.8 Dg/mm
Min: 24.1 μ
Max: 26.2 μ
Staple: 70.0 mm

