


# WINDY'S STANLEY

**AFD:** 23.7  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 20.1 %  
**CF:** 90.8 %  
**Curve:** 44.6 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 70.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# WINDY'S STANLEY

**AFD:** 23.7  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 20.1 %  
**CF:** 90.8 %  
**Curve:** 44.6 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 70.0 mm

