


# WINDY'S ZOEY

**AFD:** 25.1  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 18.3 %  
**CF:** 87.5 %  
**Curve:** 43.9 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 27.4  $\mu$   
**Staple:** 70.0 mm

% of Fibers




*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# WINDY'S ZOEY

**AFD:** 25.1  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 18.3 %  
**CF:** 87.5 %  
**Curve:** 43.9 Dg/mm  
**Min:** 23.1  $\mu$   
**Max:** 27.4  $\mu$   
**Staple:** 70.0 mm



*Alpaca Fiber Testing USA*