


# WINDY'S JAYNE


**AFD:** 21.2  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 22.0 %  
**CF:** 95.8 %  
**Curve:** 43.2 Dg/mm  
**Min:** 20.5  $\mu$   
**Max:** 22.3  $\mu$   
**Staple:** 80.0 mm



*Alpaca Fiber Testing USA*

# WINDY'S JAYNE

**AFD:** 21.2  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 22.0 %  
**CF:** 95.8 %  
**Curve:** 43.2 Dg/mm  
**Min:** 20.5  $\mu$   
**Max:** 22.3  $\mu$   
**Staple:** 80.0 mm



*Alpaca Fiber Testing USA*