


# WINDY'S MALCOLM

**AFD:** 22.9  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 20.8 %  
**CF:** 92.5 %  
**Curve:** 35.1 Dg/mm  
**Min:** 21.8  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 75.0 mm


% of Fibers



Fiber Diameter (microns)

# WINDY'S MALCOLM

**AFD:** 22.9  $\mu$   
**SD:** 4.8  $\mu$   
**CV:** 20.8 %  
**CF:** 92.5 %  
**Curve:** 35.1 Dg/mm  
**Min:** 21.8  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 75.0 mm



*Alpaca Fiber Testing USA*