


WINDY'S REBECCA

AFD: 23.5 μ
SD: 5.0 μ
CV: 21.1 %
CF: 90.7 %
Curve: 28.1 Dg/mm
Min: 20.4 μ
Max: 26.3 μ
Staple: 85.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S REBECCA

AFD: 23.5 μ
SD: 5.0 μ
CV: 21.1 %
CF: 90.7 %
Curve: 28.1 Dg/mm
Min: 20.4 μ
Max: 26.3 μ
Staple: 85.0 mm

