


SYRAH

AFD: 22.6 μ
SD: 4.7 μ
CV: 21.0 %
CF: 93.5 %
Curve: 28.5 Dg/mm
Min: 20.8 μ
Max: 24.4 μ
Staple: 105.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

SYRAH

AFD: 22.6 μ
SD: 4.7 μ
CV: 21.0 %
CF: 93.5 %
Curve: 28.5 Dg/mm
Min: 20.8 μ
Max: 24.4 μ
Staple: 105.0 mm

