


**AFD:** 23.6  $\mu$   
**SD:** 5.8  $\mu$   
**CV:** 24.5 %  
**CF:** 87.9 %  
**Curve:** 12.2 Dg/mm  
**Min:** 22.5  $\mu$   
**Max:** 25.4  $\mu$   
**Staple:** 145.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# ZIRCON

**AFD:** 23.6  $\mu$   
**SD:** 5.8  $\mu$   
**CV:** 24.5 %  
**CF:** 87.9 %  
**Curve:** 12.2 Dg/mm  
**Min:** 22.5  $\mu$   
**Max:** 25.4  $\mu$   
**Staple:** 145.0 mm

