



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sawdust Alpacas
4270 Equestrian Dr
Fallon, NV 89406-4269 US

Date: 20-Jul-20
Shear ID: 198976
Test No: 160698


Animal and Sample Description

Animal Name: KAMIAK'S KOHANA
Registry #: 31691154
Breed: Huacaya
Sex: Male
Colour: 209 - Light Brown

Date of Birth (Age): 9-Jun-02
Sample Location: GRID
Sample Date: 17-Apr-20
Previous Shear Date: 30-May-19
Total Fleece Wt (lbs): 2.70

Laboratory Data

Mean Fiber Diameter:	22.8 microns	Mean Staple Length:	56 mm
Standard Deviation:	5.8 microns	Length Standard Deviation:	2.1 mm
Coefficient of Variation:	25.6 %	Length Coefficient of Variation:	3.7 %
Spin Fineness:	23.1 microns	Mean Curvature:	45.7 deg/mm
Fibers Greater Than 30 microns:	9.2 %	SD Curvature:	25.7 deg/mm
Comfort Factor:	90.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com