



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sawdust Alpacas  
4270 Equestrian Drive, Fallon  
NV 89406-4269, US

Date: 21-Jun-23  
Shear ID: 247001  
Test No: 612571


### Animal and Sample Description

Animal Name: SAWDUST'S TUPELO  
Registry #: 35424369  
Breed: Huacaya  
Sex: Male  
Colour: 100 - White

Date of Birth (Age): 3-Sep-17  
Sample Location: GRID  
Sample Date: 17-Apr-23  
Previous Shear Date: 6-May-22  
Total Fleece Wt (lbs): 8.30

### Laboratory Data

Mean Fiber Diameter:	26.8 microns	Mean Staple Length:	86 mm
Standard Deviation:	5.4 microns	Length Standard Deviation:	1.7 mm
Coefficient of Variation:	19.9 %	Length Coefficient of Variation:	1.9 %
Spin Fineness:	25.9 microns	Mean Curvature:	45.6 deg/mm
Fibers Greater Than 30 microns:	19.6 %	SD Curvature:	18.8 deg/mm
Comfort Factor:	80.4 %	Medullated Fibers:	28.9 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)