



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sandollar Llc + Appraisal Group Sewa
2001 S Washington St. #104, Kennewick
WA 99337, USA

Date: 7-Sep-21
Shear ID: 223969
Test No: 604586


Animal and Sample Description

Animal Name: SDAF Quebracho's Miriam
Registry #: 35375227
Breed: Suri
Sex: Female
Colour: 202 - Light Fawn

Date of Birth (Age): 29-Sep-20
Sample Location: GRID
Sample Date: 24-May-21
Previous Shear Date: 24-May-20
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	16.5 microns	Mean Staple Length:	147 mm
Standard Deviation:	4.6 microns	Length Standard Deviation:	6.7 mm
Coefficient of Variation:	28.0 %	Length Coefficient of Variation:	4.6 %
Spin Fineness:	17.1 microns	Mean Curvature:	31.5 deg/mm
Fibers Greater Than 30 microns:	1.3 %	SD Curvature:	14.3 deg/mm
Comfort Factor:	98.7 %	Medullated Fibers:	6.5 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com