

Optical Fiber Diameter Analyser (OFDA100) **Micron Test Report**

ranite Ranch Ltd Red Granite Ranch Road, Livermore 536-7644, US

Date:

25-Jun-21

Shear ID:

220296

Test No:

601990

Animal and Sample Description

I Name: Red Granites Aragon

ry #:

35123040

Huacaya

Male

204 - Medium Fawn

Date of Birth (Age):

20-Aug-16

Sample Location:

GRID

Sample Date:

27-May-21

Previous Shear Date:

28-May-20

Total Fleece Wt (lbs):

6.90

Laboratory Data

Fiber Diameter: ard Deviation: cient of Variation: ineness:

Greater Than 30 microns:

rt Factor:

17.0 microns 3.8 microns

22.3 % 16.7 microns

0.4 % 99.6 %

Mean Staple Length:

Length Standard Deviation: Length Coefficient of Variation:

Mean Curvature: SD Curvature:

83 mm

3.3 mm 4.0 %

60.9 deg/mm

24.9 deg/mm

4% 2% 6% 10 15 20 30 55 60 Fiber Diameter - Microns

Test Performed According to Method AS/NZS 4492.5:2000

■Micron

Jeremy Wear **Business Manager**

loasa Kosena **Authorised Signatory**