


AFD: 26.0 μ
SD: 5.8 μ
CV: 22.4 %
CF: 80.9 %
Curve: 12.7 Dg/mm
Min: 25.6 μ
Max: 27.8 μ
Staple: 145.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

AFD: 26.0 μ
SD: 5.8 μ
CV: 22.4 %
CF: 80.9 %
Curve: 12.7 Dg/mm
Min: 25.6 μ
Max: 27.8 μ
Staple: 145.0 mm

