



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Big Timber Alpacas
19400 SW Heater Road, Sheerwood
OR 97140, US

Date: 15-Jun-23
Shear ID: 249572
Test No: 612519


Animal and Sample Description

Animal Name: BIG TIMBER's ICED SAKURA
Registry #: 35587101
Breed: Suri
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 18-May-18
Sample Location: GRID
Sample Date: 25-May-23
Previous Shear Date: 24-May-22
Total Fleece Wt (lbs): 6.8

Laboratory Data

Mean Fiber Diameter:	26.0 microns	Mean Staple Length:	134 mm
Standard Deviation:	6.8 microns	Length Standard Deviation:	6.3 mm
Coefficient of Variation:	26.3 %	Length Coefficient of Variation:	4.7 %
Spin Fineness:	26.6 microns	Mean Curvature:	31.3 deg/mm
Fibers Greater Than 30 microns:	21.7 %	SD Curvature:	17.7 deg/mm
Comfort Factor:	78.3 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com