


# ELECTROFYRE'S TANYA

**AFD:** 23.3  $\mu$   
**SD:** 5.2  $\mu$   
**CV:** 22.0 %  
**CF:** 90.2 %  
**Curve:** 15.2 Dg/mm  
**Min:** 20.2  $\mu$   
**Max:** 27.0  $\mu$   
**Staple:** 0.0 mm

% of Fibers




*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# ELECTROFYRE'S TANYA

**AFD:** 23.3  $\mu$   
**SD:** 5.2  $\mu$   
**CV:** 22.0 %  
**CF:** 90.2 %  
**Curve:** 15.2 Dg/mm  
**Min:** 20.2  $\mu$   
**Max:** 27.0  $\mu$   
**Staple:** 0.0 mm



*Alpaca Fiber Testing USA*