


JASMINE

AFD: 20.5 μ
SD: 4.6 μ
CV: 22.5 %
CF: 96.6 %
Curve: 11.4 Dg/mm
Min: 19.7 μ
Max: 22.1 μ
Staple: 110.0 mm

% of Fibers




Alpaca Fiber Testing USA

Fiber Diameter (microns)

JASMINE

AFD: 20.5 μ
SD: 4.6 μ
CV: 22.5 %
CF: 96.6 %
Curve: 11.4 Dg/mm
Min: 19.7 μ
Max: 22.1 μ
Staple: 110.0 mm



Alpaca Fiber Testing USA