



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas  
9200 Spooner Creek Ln  
Blaine, WA 98230 US

Date: 27-Jul-20  
Shear ID:  
Test No: 200761


### Animal and Sample Description

Animal Name: Sunny Accoyo Modoc  
Registry #: 35532408  
Breed: Huacaya  
Sex: Female  
Colour: 205 - Dark Fawn

Date of Birth (Age): 08/04/2019  
Sample Location: GRID  
Sample Date:  
Previous Shear Date: 31-Aug-19  
Total Fleece Wt (lbs): 3.90

### Laboratory Data

Mean Fiber Diameter:	15.6 microns	Mean Staple Length:	79 mm
Standard Deviation:	3.9 microns	Length Standard Deviation:	6.4 mm
Coefficient of Variation:	24.8 %	Length Coefficient of Variation:	8.1 %
Spin Fineness:	15.7 microns	Mean Curvature:	60.1 deg/mm
Fibers Greater Than 30 microns:	0.3 %	SD Curvature:	29.3 deg/mm
Comfort Factor:	99.7 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)