



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Fiber Meadow Alpacas
26417 Minklier Rd, Sedro Woolley
WA 98284, US

Date: 14-Feb-23
Shear ID:
Test No: 611190


Animal and Sample Description

Animal Name: KENTUCKY BULLEIT
Registry #: 35140191
Breed: Huacaya
Sex: Male
Colour: 202 - Light Fawn

Date of Birth (Age): 12-Jun-16
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	20.1 microns	Mean Staple Length:	73 mm
Standard Deviation:	4.5 microns	Length Standard Deviation:	2.4 mm
Coefficient of Variation:	22.4 %	Length Coefficient of Variation:	3.3 %
Spin Fineness:	19.8 microns	Mean Curvature:	56.5 deg/mm
Fibers Greater Than 30 microns:	2.0 %	SD Curvature:	24.8 deg/mm
Comfort Factor:	98.0 %	Medullated Fibers:	16.6 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com