



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Dean & Pamela Hiestand
26417 Minkler Rd,
Sedro Woolley, WA 98284 USA

Date: 25-Nov-20
Shear ID:
Test No: 501246


Animal and Sample Description

Animal Name: Fiber Meadows Carbon's Shadow
Registry #: 35414537
Breed: Huacaya
Sex: Female
Colour: True Black

Date of Birth (Age):
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	21.7 microns	Mean Staple Length:	105 mm
Standard Deviation:	4.5 microns	Length Standard Deviation:	5.1 mm
Coefficient of Variation:	20.8 %	Length Coefficient of Variation:	4.9 %
Spin Fineness:	21.1 microns	Mean Curvature:	34.0 deg/mm
Fibers Greater Than 30 microns:	4.2 %	SD Curvature:	19.0 deg/mm
Comfort Factor:	95.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com