



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

FLYING IRON RANCH ALPACAS
9110 Rockbrook Dr
Dallas, TX 7520-3907 US

Date: 20-Aug-20
Shear ID: 205206
Test No: 200318


Animal and Sample Description

Animal Name: XANADU CLANDESTINE
Registry #: 31573863
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 18-May-09
Sample Location: GRID
Sample Date: 26-May-20
Previous Shear Date: 8-May-19
Total Fleece Wt (lbs): 6.10

Laboratory Data

Mean Fiber Diameter:	22.9 microns	Mean Staple Length:	74 mm
Standard Deviation:	4.5 microns	Length Standard Deviation:	1.3 mm
Coefficient of Variation:	19.7 %	Length Coefficient of Variation:	1.8 %
Spin Fineness:	22.0 microns	Mean Curvature:	36.6 deg/mm
Fibers Greater Than 30 microns:	4.9 %	SD Curvature:	21.9 deg/mm
Comfort Factor:	95.1 %	Medullated Fibers:	10.5 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com