



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Nancy Pulse and/or Robert Pulse  
1154 County Road 4360  
Decatur, TX 76234-5199 US

Date: 11-Aug-20  
Shear ID: 201278  
Test No: 198570


### Animal and Sample Description

Animal Name: SNOWMASS LOVE'S VALOR  
Registry #: 35487081  
Breed: Huacaya  
Sex: Male  
Colour: 100 - White

Date of Birth (Age): 23-Jun-18  
Sample Location: GRID  
Sample Date: 23-Mar-20  
Previous Shear Date: 9-May-19  
Total Fleece Wt (lbs): 6.20

### Laboratory Data

Mean Fiber Diameter:	18.6 microns	Mean Staple Length:	88 mm
Standard Deviation:	2.6 microns	Length Standard Deviation:	3.6 mm
Coefficient of Variation:	14.0 %	Length Coefficient of Variation:	4.1 %
Spin Fineness:	17.2 microns	Mean Curvature:	41.9 deg/mm
Fibers Greater Than 30 microns:	0.1 %	SD Curvature:	18.4 deg/mm
Comfort Factor:	99.9 %	Medullated Fibers:	7.2 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)