


PRISSY

AFD: 18.3 μ
SD: 3.9 μ
CV: 21.5 %
CF: 99.4 %
Curve: 32.6 Dg/mm
Min: 16.6 μ
Max: 20.3 μ
Staple: 90.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

PRISSY

AFD: 18.3 μ
SD: 3.9 μ
CV: 21.5 %
CF: 99.4 %
Curve: 32.6 Dg/mm
Min: 16.6 μ
Max: 20.3 μ
Staple: 90.0 mm

